

DESCRIPTION

PENEBAR™ PRIMER enhances the bonding between preformed sealants, like PENEBAR™ SW, and concrete surfaces aiding in the installation process. Conveniently applied at the job site.

RECOMMENDED FOR

PENEBAR™ PRIMER should be applied to the substrate by brush prior to installation of PENEBAR™ SW preformed joint sealer.

DIRECTIONS FOR USE

Carefully brush off all dust and debris and brush apply a coat of PENEBAR™ PRIMER to the area where PENEBAR™ SW preformed joint sealer is to be placed.

PHYSICAL PROPERTIES

Color: Bright Orange

% Solids: 20% minimum

Solvent Type: Water

Flash Point: 200°F (93°C) minimum

Dry Time @ 77°F (25°C): 10 minutes

Dry Time @ 40°F (4°C): 60 minutes

Clean Up: Soap and Water

Coverage per Gallon: Approximately 400 sq ft (37 m²) on wet cast concrete. Coverage diminishes on dry cast concrete.

Appropriate Substrates: Concrete, Plastic, Metal

Min. Storage Temperature: 40°F (4°C). Product should not be allowed to freeze.

Min. Application Temperature: 20°F (-7°C)

Surface when Dry: Tacky

PACKAGING

PENEBAR™ PRIMER is available in 1-gallon (3.8 L) pails.

STORAGE / SHELF LIFE

When stored in a dry enclosed area off the ground at a minimum temperature of 45°F (7°C) in unopened, undamaged pails, shelf life is unlimited.

SAFE HANDLING INFORMATION

Keep out of reach of children.

WARRANTY

PENETRON INTERNATIONAL, LTD. warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to PENETRON INTERNATIONAL, LTD. shall be limited to replacement of the material proven to be defective and shall in no case be liable otherwise or for incidental or consequential damages. **PENETRON INTERNATIONAL, LTD. MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED.** User shall determine the suitability of the product for his intended use and assume all risks and liability in connection therewith.

v. D04

Penetron International, Ltd.
45 Research Way, Suite 203
East Setauket, NY 11733, USA
+1 (631) 941-9700
penetron.com
info@penetron.com